

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : A61K 47/10, 47/32, 47/36, 38/18	A2	(11) International Publication Number: WO 00/13710 (43) International Publication Date: 16 March 2000 (16.03.00)
(21) International Application Number: PCT/US99/20382 (22) International Filing Date: 3 September 1999 (03.09.99) (30) Priority Data: 60/099,168 4 September 1998 (04.09.98) US (71) Applicant (for all designated States except US): SCIOS INC. [US/US]; 820 West Maude Avenue, Sunnyvale, CA 94086 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): JENNINGS, Robert, N., Jr. [US/US]; 5536 Blossom Dale Drive, San Jose, CA 95124 (US). YANG, Bing [CN/US]; 802 Kraken Lane, Redwood City, CA 94065 (US). PROTTER, Andrew, A. [US/US]; 185 California, Palo Alto, CA 94301 (US). WANG, Yu-Chang, John [US/US]; 1421 Baypoint Drive, Newport Beach, CA 92660 (US). (74) Agent: DREGER, Ginger, R.; Knobbe, Martens, Olson and Bear, LLP, 16th Floor, 620 Newport Center Drive, Newport Beach, CA 92660 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: HYDROGEL COMPOSITIONS FOR THE CONTROLLED RELEASE ADMINISTRATION OF GROWTH FACTORS		
(57) Abstract Compositions and methods are disclosed for the controlled release delivery of polypeptide growth factors. The compositions of the invention are hydrogels which comprise: a polypeptide growth factor having at least one region of positive charge; a physiologically acceptable water-miscible anionic polymer; a physiologically acceptable non-ionic polymeric viscosity controlling agent; and water.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

5 **HYDROGEL COMPOSITIONS FOR THE CONTROLLED RELEASE**
 ADMINISTRATION OF GROWTH FACTORS

10 **BACKGROUND OF THE INVENTION**

 This invention relates to formulations for the controlled delivery of growth factors. In specific embodiments, the invention relates to controlled release delivery of angiogenic growth factors for the treatment of ischemic tissue and/or for wound healing.

15 Polypeptide growth factors regulate the growth and proliferation of cells. A number of human growth factors have been identified and characterized. Merely by way of example, these include basic fibroblast growth factor (bFGF), acidic fibroblast growth factor (aFGF), vascular endothelial cell growth factor (VEGF), platelet derived growth factor (PDGF), insulin-like growth factors (IGF-I and IGF-II), nerve growth factor
20 (NGF), epidermal growth factor (EGF) and heparin-binding EGF-like growth factor (HBEGF). Because of their ability to stimulate cell growth and proliferation, growth factors have been used as wound healing agents. Some growth factors, such as bFGF and VEGF exhibit potent angiogenic effects, i.e. they stimulate the growth of new capillary vessels. These angiogenic growth factors have been used to treat conditions associated
25 with ischemia, such as coronary artery disease and peripheral vascular disease. By treating ischemic tissue with an angiogenic growth factor, new blood vessels are generated which are capable of bypassing occluded segments of arteries, thereby reestablishing blood flow to the affected tissue (a procedure sometimes referred to as a "bio-bypass"). Angiogenic growth factors have also been used to promote wound
30 healing.

A major challenge in the use of growth factors is the development of a delivery vehicle which will provide the appropriate level of bioavailability of the drug to the affected area to achieve a desired clinical result. Hence, U.S. Patent No. 5,457,093 discloses the use of various agents to produce relatively high viscosity hydrogels containing growth factors. We have found, however, that the use of a hydrogel containing bFGF and hydroxyethyl cellulose failed to produce a desired result in a human clinical trial directed at topical wound healing despite the fact that bFGF is a potent angiogenic agent and possesses other biological activities that are desirable in a wound healing agent. Additionally, we have found that the use of a hydrogel containing bFGF and a polyoxyethylene-polyoxypropylene block copolymer (Pluronic) in an animal model of angiogenesis failed to produce a desired angiogenic response.

Another problem that has been encountered in the preparation of controlled release formulations of polypeptide growth factors is that the excipients employed to impart controlled release characteristics may make it difficult to prepare an homogeneous dispersion of the growth factor by simple mixing techniques. For example, a topical formulation of PDGF has been produced commercially using greater than 1% carboxymethylcellulose. At such concentrations, obtainment of an homogeneous dispersion of the polypeptide is difficult.

It is an object of the invention to provide a formulation for the controlled release delivery of polypeptide growth factors which releases the growth factor at a rate which promotes angiogenesis and/or wound healing.

It is another object of the invention to provide methods for administering growth factors at controlled rates capable of promoting wound healing and/or angiogenesis in a subject in need of such treatment.

It is a further object of the invention to provide controlled release formulations of polypeptide growth factors that can be prepared as homogeneous compositions by simple mixing techniques.

Other objects of the invention will be apparent from the description which follows.

SUMMARY OF THE INVENTION

5

In accordance with the present invention, there is provided a hydrogel composition for the controlled release delivery of a polypeptide growth factor comprising:

- (a) a therapeutically effective amount of a polypeptide growth factor having at least one region of positive charge;
- 10 (b) a physiologically acceptable water-miscible anionic polymer;
- (c) a physiologically acceptable water-miscible non-ionic polymeric viscosity controlling agent; and
- (d) water.

15 We have discovered that the use of an anionic polymer in combination with a non-ionic polymeric viscosity controlling agent allows one to control independently the drug release characteristics and the physical characteristics, i.e. viscosity, of the formulation. In particular, we have discovered that the water-miscible anionic polymer can be used to impart a therapeutically efficacious release rate when used at low concentrations.

20 Preferably, the water-miscible anionic polymer is selected from sodium carboxymethylcellulose and poly(acrylic acid). Poly(acrylic acid) imparts a therapeutically efficacious release rate when it constitutes as little as 0.001% to 0.01% by weight of the total hydrogel composition. At this low concentration, poly(acrylic acid) does not contribute significantly to an increase in viscosity of the formulation. Thus, one
25 can use the poly(acrylic acid) to optimize the release rate of the growth factor in order to obtain a desired biological effect while employing the physiologically acceptable non-ionic polymer to obtain a desired viscosity for use in a particular application. While one may produce a highly viscous hydrogel in accordance with the invention, we have found that high viscosity is not necessary in order to obtain a desired biological effect in wound
30 healing or angiogenesis.

In one embodiment of the invention, there is provided a method for treating a condition characterized by ischemia wherein the composition of the invention is employed to administer a controlled release dosage of an angiogenic growth factor such as bFGF or VEGF to the ischemic tissue. This method can be used, for example, to treat coronary artery disease or peripheral vascular disease.

In another embodiment of the invention, there is provided a method for promoting wound healing wherein the composition of the invention is employed to administer a controlled release dosage of a growth factor to the wound site.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a graphic representation of the effect of a bFGF-containing hydrogel formulation of the invention on granulation tissue accumulation in an ischemic rabbit ear wound healing model.

Fig. 2 is a graphic representation of the effect of a bFGF-containing hydrogel formulation of the invention on epitheal tissue accumulation in an ischemic rabbit ear wound healing model.

Fig. 3 is a graphic representation of the effect of a bFGF-containing hydrogel formulation of the invention on granulation tissue gap in ischemic rabbit ear wounds.

Fig. 4 is a graphic representation of the effect of a bFGF-containing hydrogel formulation of the invention on epithelial tissue gap in ischemic rabbit ear wounds.

Fig. 5 illustrates the release of bFGF from gel formulations containing 0.4mg/mL bFGF. A: 10% Pluronic® and 0.8% CMC; B: 10% Pluronic® and 0.001% Carbopol®; C: 10% Pluronic®.

Fig. 6 illustrates the release of bFGF from gel formulations containing 4.0 mg/mL bFGF. A: 10% Pluronic® and 0.8% CMC; B: 10% Pluronic® and 0.001% Carbopol®; C: 10% Pluronic®.

DETAILED DESCRIPTION OF THE INVENTION

The compositions of the invention can be used for the controlled release delivery of a polypeptide growth factor having at least one region of net positive charge. By "at least one region of net positive charge" is meant that the polypeptide growth factor has a net overall positive charge or has at least one positively charged domain which is capable of interacting with the anionic polymer in such a way as to attenuate the release of the growth factor from the composition. Merely by way of example, one can mention as growth factors suitable for use in the composition of the invention basic fibroblast growth factor (bFGF, including without the limitation the 155-, 154- and 146-amino acid forms), vascular endothelial cell growth factor (VEGF, including without limitation the 189-, 165-, 145-, 121- and 110-amino acid forms), platelet derived growth factor (PDGF), epidermal growth factor (EGF) and heparin binding EGF-like growth factor (HB-EGF). The human amino acid sequences are known for all of these growth factors. VEGF and bFGF belong to a class of growth factors which exhibit angiogenic effects, i.e. they promote the growth of new capillary blood vessels. The process of angiogenesis is an important component of wound healing. Additionally, these polypeptides have been employed to treat conditions characterized by ischemia. Administration of an angiogenic factor to ischemic tissue causes the formation of new capillaries which can bypass an obstructed artery and reestablish blood flow to the affected tissue.

The polypeptide growth factor is employed in a therapeutically effective amount. The specific amount of growth factor employed in the composition will vary with the specific growth factor, the condition being treated and the dosing regimen. Those of ordinary skill in the art will be able to determine an appropriate amount of growth factor to employ in the composition. Generally, the amount may vary from about 0.01% to about 5% by weight of the composition.

The composition of the invention also contains a physiologically acceptable water-miscible anionic polymer. Suitable polymers include, by way of example, poly(acrylic acid), sodium carboxymethylcellulose, alginic acid and hyaluronic acid. Poly(acrylic acid) and sodium carboxymethylcellulose are preferred anionic polymers, with
5 poly(acrylic acid) being most preferred. The anionic polymer employed may have a molecular weight from about 5,000 Da to about 5,000,000 Da.

Generally, the water-miscible anionic polymer can be employed in an amount from about 0.001% to about 1% based on the total weight of the composition. The
10 amount of water-miscible anionic polymer employed in the composition may vary depending, in part, on the specific polymer employed. Since the charge density of the anionic polymer is a determinative factor in the release rate, anionic polymers having a relatively high charge density (and a concomitantly stronger interaction with the polypeptide growth factor) can be employed at lower concentrations in the formulation
15 and still provide effective control over release rate. For example, sodium carboxymethylcellulose has a lower density of negative charge than poly(acrylic acid). Accordingly, poly(acrylic acid) can be effectively employed at considerably lower concentrations than sodium carboxymethylcellulose.

When using poly(acrylic acid) as the water-miscible anionic polymer, it is
20 preferred to employ the poly(acrylic acid) at low concentrations; i.e. from about 0.001% to about 0.1% by weight of the composition. Surprisingly, we have found that the poly(acrylic acid) at these low concentrations is capable of effecting release at a rate which promotes a desirable biological response. Higher poly(acrylic acid) concentrations,
25 i.e. as high as about 1.0%, which also cause a positive biological response, were found to be also associated with an inflammatory response. Furthermore, at higher concentrations, poly(acrylic acid) may contribute to the viscosity of the composition.

Due to its lower charge density, sodium carboxymethylcellulose is preferably
30 employed at a somewhat higher concentration, i.e. from about 0.1% to about 1% based on the total weight of the composition.

The composition of the invention also contains a physiologically acceptable non-ionic polymeric viscosity controlling agent. The non-ionic polymeric viscosity controlling agent can have a molecular weight from about 5,000 Da to about 15,000 Da.

5 A preferred non-ionic polymeric viscosity controlling agent is a polyoxyethylene-polyoxypropylene block copolymer. Such copolymers consist of segments, or blocks, of polymerized ethylene oxide units, and segments, or blocks, of polymerized propylene oxide units. They are commercially available in a range of molecular weights suitable for use in the compositions of the invention. For example, we have employed a block
10 copolymer of the A-B-A type (polyethylene oxide-polypropylene oxide-polyethylene oxide) having a molecular weight of about 12,600, which is commercially available under the trademark Pluronic® F-127. Such a copolymer provides the advantage that its viscosity increases with temperature. Accordingly, one can prepare a composition of the invention which is relatively free-flowing at room temperature and easily prepared by
15 mixing, but increases in viscosity when exposed to body temperature, thereby preventing the composition from flowing away from the desired area of application.

The amount of the polymeric viscosity controlling agent employed may vary considerably depending on the desired viscosity for the particular application. We have
20 found that obtaining satisfactory controlled release of the growth factor does not depend on the viscosity of the composition (although increased viscosity may slow the release rate). The compositions of the invention can range from free-flowing liquids to viscous gels at room temperature. The polymeric viscosity controlling agent may be present from about 0.5% to about 25% by weight of the total composition, preferably 5 to 20%. For
25 some applications, such as topical wound healing, relatively high viscosity may be desired in order to prevent migration of the growth factor from the treatment area. For such applications, one would employ a sufficient amount of the non-ionic polymeric viscosity controlling polymer such that the composition will remain in place at the site of applications.

30

The compositions of the invention may also contain other conventional pharmaceutical excipients and additives in the usual effective amounts. These may

include, for example, preservatives, anti-microbial agents, buffering agents, tonicity agents, surfactants, anti-oxidants, chelating agents and protein stabilizers (e.g., sugars).

The formulations of the invention can be produced by mixing the ingredients.

5 Advantageously, a stock gel may be produced by mixing the non-ionic, polymeric viscosity controlling agent, at the desired concentration, by simple mixing. The anionic polymer is then dissolved in the stock gel solution and an aqueous solution of the growth factor is then dissolved in the gel and/or the gel can be used to reconstitute a freeze dried powder containing growth factor.

10

The compositions of the invention are useful in promoting wound healing in an individual, e.g. a human or other mammal. The wounds that can be treated with the compositions of the invention include any wounds caused by accidental injury, surgical trauma or disease processes. These include cutaneous wounds such as burn wounds,
15 incisional wounds, donor site wounds from skin transplants, ulcers, including pressure sores, venous stasis ulcers and diabetic ulcers; ophthalmic wounds such as corneal ulcers, radial keratotomy, corneal transplant, epikeratophakia and other surgically induced ophthalmic wounds; and internal wounds such as internal surgical wounds and ulcers.

20

Application of the composition to the wound site may be performed in a variety of ways, depending on the type of the wound and the consistency of the composition. In the case of a relatively viscous composition, the composition may be applied in the manner of a salve or ointment. In the case of more free-flowing composition, the composition may also be applied by injection or as drops, e.g. eye drops. The composition may also be
25 employed to impregnate a dressing material, in the case of topical application, or an implant material, preferably a biodegradable implant material, in the case of application for internal wound healing. The composition may be delivered in a single application or in multiple applications as needed to deliver a therapeutic dosage, as determined by the wound healing response.

30

Compositions of the invention containing angiogenic growth factors, e.g. bFGF or VEGF, can be used to treat conditions characterized by ischemia in order to restore blood

flow to the affected area. Such conditions include coronary artery disease and peripheral vascular disease. The composition is applied to the affected tissue, for example by injection into the desired area or by use of an implant, in a single or multiple application as needed to achieve a therapeutic dose, as determined by the angiogenic response.

5

The following examples are provided in order to further illustrate the practice of the invention and are not intended to limit the scope of the invention in any way.

EXAMPLES

10

In the following examples, the sodium carboxymethylcellulose (CMC) employed had a molecular weight of 70,000 Da. The poly(acrylic acid) had a molecular weight of 3,000,000 Da (sold under the trademark Carbopol®). The polyoxyethylene-polyoxypropylene block copolymer employed as a copolymer of the A-B-A type (polyoxyethylene-polyoxypropylene-polyoxyethylene) having a molecular weight of 12,600 (sold under the trademark Pluronic® 127). The basic fibroblast growth factor (bFGF) employed was recombinantly produced human basic fibroblast growth factor, the expression product of a gene encoding the 155-amino acid form of the protein.

15

20 EXAMPLE 1: Gel formulation preparation

1. Preparation of 11.25% polyoxyethylene-polyoxypropylene stock solution.

In a 250 mL volumetric flask, 28.125 g of polyoxyethylene-polyoxypropylene was dissolved in a 20 mM citrate buffer with 1 mM EDTA (pH 6.0). The solution was mixed by agitation and placed in a 4°C refrigerator until the polymer was dissolved completely.

25

2. Preparation of 0.9% CMC and 11.25% polyoxyethylene-polyoxypropylene stock gel solution.

30

In a glass bottle, 0.9 g of sodium carboxymethylcellulose was dissolved in 100 mL of 11.25% polyoxyethylene-polyoxypropylene stock gel solution prepared as described above. The solution was mixed by agitation and placed in a 4°C refrigerator.

- 5 3. Preparation of 0.001% poly(acrylic acid) and 11.25% polyoxyethylene-polyoxypropylene stock gel solution.

10 In a glass bottle, 1 mg of poly(acrylic acid) was dissolved in 100 mL of 11.25% polyoxyethylene-polyoxypropylene stock gel solution prepared as described above. The solution was mixed by agitation and placed in a 4°C refrigerator.

4. Preparation of a 4.0 mg/mL bFGF gel formulation in 10% polyoxyethylene-polyoxypropylene and 0.8% sodium carboxymethylcellulose.

15 One vial of lyophilized bFGF (7.2 mg/vial) was reconstituted with 1.6 mL (1.8 mL total volume) of the stock gel solution (0.9% CMC and 11.25% polyoxyethylene-polyoxypropylene) to give a gel formulation with 4.0 mg/mL bFGF, 10% polyoxyethylene-polyoxypropylene and 0.8% CMC. The formulation was mixed by agitation until the powder was completely dissolved.

20

5. Preparation of 0.4 mg/mL bFGF gel formulation in 10% polyoxyethylene-polyoxypropylene and 0.8% CMC.

25 One vial of lyophilized bFGF (7.2 mg/vial) was reconstituted with 1.8 mL (2.0 mL total volume) of water. One mL of the reconstituted bFGF solution was added to 8.0 mL of the stock gel solution (0.9% CMC and 11.25% polyoxyethylene-polyoxypropylene) to give a gel formulation with 0.4 mg/mL bFGF, 10% polyoxyethylene-polyoxypropylene and 0.8% CMC. The gel formulation was mixed by agitation until the powder was completely dissolved.

30

6. Preparation of 4.0mg/mL bFGF gel in 10% polyoxyethylene-polyoxypropylene and 0.01% poly(acrylic acid).

The preparation procedure was the same as the preparation of 4.0 mg/mL bFGF gel formulation in 10% polyoxyethylene-polyoxypropylene and 0.8% CMC except the stock gel formulation was 0.01% poly(acrylic acid) and 11.25% polyoxyethylene-polyoxypropylene.

7. Preparation of 0.4 mg/mL bFGF gel in 10% polyoxyethylene-polyoxypropylene and 0.01% poly(acrylic acid).

The preparation procedure was the same as the preparation of 0.4 mg/mL bFGF gel formulation in 10% polyoxyethylene-polyoxypropylene and 0.8% CMC except that the stock gel formulation was 0.01% poly(acrylic acid) and 11.25% polyoxyethylene-polyoxypropylene.

Using the procedures described in this Example 1, one can prepare formulations of the invention containing varying amounts of growth factor, water-miscible anionic polymer and water-miscible non-ionic polymer.

EXAMPLE 2: Promotion of Angiogenesis

Male and female Sprague-Dawley rats (225-425 g body weight) were briefly anesthetized by inhalation of isoflurane. The abdominal area was shaved and cleaned with 70% ethanol. Using an 18- or 25-gauge needle, gel formulations containing varying dosages of bFGF, produced by procedures as described in Example 1, as well as control gel formulations containing no bFGF, were injected subcutaneously along the mid-line of the abdominal area. Animals were alert and mobile almost immediately after inhalation of isoflurane was discontinued.

Five days after injection, animals were euthanized by carbon dioxide inhalation or phenobarbital overdose. Body weight was recorded and the abdominal skin was gently incised and reflected to expose the abdominal muscle. The tissue immediately

surrounding the injection site was rated for angiogenesis, as well as for presence or absence of inflammation. The scoring system was as follows:

- 5 + + + + Substantial angiogenesis
 + + + Moderate angiogenesis
 + + + Slight angiogenesis
 + Very slight angiogenesis
 - No angiogenesis
 I Inflammation

10 Results of the 5-day angiogenesis tests are presented in the table below.

Angiogenesis Result of bFGF Gel Formulations (5 days test)

bFGF (mg/mL)	Polyoxyethylene- Polyoxypropylene (Pluronic 127)	Anionic Polymer	Result
0.4	17%		-
4.0	10%	0.80% CMC	++++
0.4	10%	0.80% CMC	+++
0.04	10%	0.80% CMC	++
0	10%	0.80% CMC	-
0.4	15%	0.50% PAA	++++, I
0.4	10%	0.78% PAA	++++, I
4.0	10%	0.80% PAA	+++++, I
0.4	10%	0.80% PAA	++++, I
0.04	10%	0.80% PAA	++++, I
0	10%	0.80% PAA	+, I
0.4	10%	0.25% PAA	+++ , I
0.4	10%	0.10% PAA	+++ , I
0	10%	0.25% PAA	+, I
0	10%	0.10% PAA	+, I
0.4	10%	0.01% PAA	+++
0.4	10%	0.001% PAA	+++
0	10%	0.01% PAA	-
0	10%	0.001% PAA	-

PAA = poly(acrylic acid)

CMC = sodium carboxymethylcellulose

5

EXAMPLE 3: Promotion of wound healing.

Dr. Thomas Mustoe (Division of Plastic Surgery and Departments of Surgery and Pathology, Northwestern University Medical School, Chicago) has demonstrated that

10 ischemia in the rabbit ear, induced by surgical transection of two of the three major ear

arteries, results in impaired healing of full thickness skin wounds (Ahn and Mustoe, *Ann Plast Surg* 24:17-23 (1990)). As the wound is splinted by the underlying intact cartilage of the ear, wound closure occurs by cellular infiltration and not by physical contraction. Published studies have shown that bFGF administered in saline at doses up to 30 µg/wound is ineffective in stimulating the accumulation of granulation tissue or epithelial tissue in these wounds (Wu et al., *Growth Factors* 12:29-35 (1995)). The effects of bFGF delivered in a sustained release gel formulation was tested in this model.

Two dosage forms of bFGF (0.4 mg/mL and 4.0 mg/mL) formulated with 10% polyoxyethylene-polyoxypropylene (Pluronic® 127) plus 0.001% polyacrylic acid were tested with placebo controls (formulation without bFGF) in a blinded manner. Each dosage form was applied at 10 µL per wound (4 and 40 µg/wound bFGF). Test samples were applied once on the day the wound was made. Histological assessment, made after 7 days of recovery, included quantitation of granulation tissue and epithelial tissue accumulation (Wu et al., 1995). There was a significant accumulation of granulation tissue (represented in Fig. 1) and epithelial tissue (represented in Fig. 2) in the wound area in response to bFGF. In addition, the wound size, measured in terms of the granulation tissue gap (represented in Fig. 3) and the epithelial tissue gap (represented in Fig. 4) was reduced in a statistically significant manner by bFGF treatment using the formulation of the invention. The P values indicated in Fig. 1-4 were derived by a two-tailed unpaired t-test. Previous work has shown that doses of bFGF up to 30 µg/wound formulated in saline were ineffective in this model.

EXAMPLE 4: *In vitro* release of bFGF

25

The *in vitro* release of bFGF from various gel formulations was evaluated using Franz diffusion cells (Model FDC40015FG, Crown Bioscientific, Inc., NJ) at 32°C. Each cell consists of a donor and receiving chamber. A hydrophilic membrane (Nucleopore Track-Etch Membrane, Corning Separation Division, No. 110609) was mounted between the donor and receiving chambers. The membrane was chosen to allow bFGF, but no significant amounts of Pluronic®, Carbopol®, or sodium CMC to cross into the receiving chamber. Gel formulations were placed in the donor chamber and a buffer solution

(100 g/ml heparin in HBS-EP buffer [BIA certified, Biacore AB, Uppsala, Sweden, containing 0.01M HEPES at pH 7.4, 0.15 M NaCl, 3 mM EDTA and 0.05% Polysorbate 20]) was placed in the receiving chamber. Samples were withdrawn from the receiving chamber at various times and the bFGF concentrations were determined using a BiaCore 2000 instrument (Biacore AB, Uppsala, Sweden). The cumulative amount and cumulative percent released were then calculated, and the results are shown in Figures 5 and 6, respectively.

Claims:

1. A hydrogel composition for the controlled release delivery of a polypeptide growth factor comprising:
 - 5 (a) a therapeutically effective amount of a polypeptide growth factor containing at least one region of positive charge;
 - (b) a physiologically acceptable water-miscible anionic polymer;
 - (c) a physiologically acceptable water-miscible non-ionic polymeric viscosity controlling agent; and
 - 10 (d) water.
2. A composition as claimed in claim 1, wherein said growth factor is selected from basic fibroblast growth factor, platelet derived growth factor, epidermal growth factor, vascular endothelial cell growth factor and heparin binding EGF-like growth factor.
- 15 3. A composition as claimed in claim 1, wherein said growth factor is basic fibroblast growth factor.
- 20 4. A composition as claimed in claim 1, wherein said water-miscible anionic polymer is selected from sodium carboxymethylcellulose and poly(acrylic acid).
5. A composition as claimed in claim 1, wherein said water-miscible anionic polymer is poly(acrylic acid).
- 25 6. A composition as claimed in claim 1, wherein said water-miscible non-ionic polymeric viscosity controlling agent is a polyoxyethylene-polyoxypropylene block copolymer having a molecular weight from 5,000 Da to about 15,000 Da.
- 30 7. A composition as claimed in claim 1, wherein said anionic polymer is present in an amount from about 0.001% to about 1.0% by weight of said composition.

8. A composition as claimed in claim 5, wherein said poly(acrylic acid) is present in an amount from about 0.001% to about 0.1% by weight of said composition.

5 9. A composition as claimed in claim 5, wherein said poly(acrylic acid) is present in an amount from about 0.001% to about 0.01% by weight of said composition.

10 10. A composition as claimed in claim 6, wherein said non-ionic polymeric viscosity controlling agent is present in an amount from about 0.5% to about 25% by weight of said composition.

11. A hydrogel composition for the controlled release administration of basic fibroblast growth factor, which comprises:

- 15 (a) a therapeutically effective amount of basic fibroblast growth factor;
- (b) from about 0.001% to about 0.1% by weight physiologically acceptable, water-miscible anionic polymer;
- (c) from about 0.5% to about 25% by weight non-ionic, water-
- 20 miscible polymeric viscosity controlling agent; and
- (d) water.

12. A method for the controlled release delivery of a growth factor comprising administering to an individual in need of treatment with such growth factor a

25 hydrogel composition comprising:

- (a) a therapeutically effective amount of a polypeptide growth factor having at least one region of positive charge;
- (b) a physiologically acceptable water-miscible anionic polymer;
- 30 (c) a physiologically acceptable water-miscible non-ionic polymeric viscosity controlling agent; and
- (d) water.

13. A method as claimed in claim 12, wherein said growth factor is selected from basic fibroblast growth factor, platelet derived growth factor, epidermal growth factor, vascular endothelial cell growth factor and heparin binding EGF-like growth factor.

5

14. A method as claimed in claim 12, wherein said growth factor is basic fibroblast growth factor.

15. A method as claimed in claim 12, wherein said anionic polymer is selected from sodium carboxymethylcellulose and poly(acrylic acid).

10

16. A method as claimed in claim 12, wherein said non-ionic polymeric viscosity controlling agent is a polyoxyethylene-polyoxypropylene block copolymer.

15

17. A method as claimed in claim 12, wherein the anionic polymer is present in an amount from about 0.001% to about 0.1% by weight of the composition.

18. A method as claimed in claim 12, wherein the non-ionic polymeric viscosity controlling agent is present in an amount from about 0.5% to about 25% by weight of the composition.

20

19. A method for promoting wound healing which comprises administering to an individual in need of such treatment of a controlled release hydrogel composition comprising:

25

(a) a therapeutically effective amount of basic fibroblast growth factor;

(b) from about 0.001% to about 0.1% by weight physiologically acceptable, water-miscible anionic polymer;

30

(c) from about 0.5% to about 25% by weight non-ionic, water-miscible polymeric viscosity controlling agent; and

(d) water.

20. A method as claimed in claim 12, wherein the hydrogel composition is administered by depot injection.

21. A method as claimed in claim 12, wherein the hydrogel composition is administered topically.

22. A method for producing a controlled release growth factor composition which comprises dispersing in water:

- (a) a physiologically acceptable, water miscible, non-ionic polymeric viscosity controlling agent;
- (b) a sufficient amount of a physiologically acceptable, water miscible, anionic polymer to impart controlled release of the growth factor from the composition; and
- (c) a therapeutically effective amount of polypeptide growth factor having at least one region of positive charge.

23. A method of treating ischemia which comprises administering to a region of ischemic tissue in a subject suffering from a condition characterized by ischemia a controlled release hydrogel composition comprising:

- (a) a therapeutically effective amount of an angiogenic polypeptide growth factor having at least one region of positive charge;
- (b) a physiologically acceptable water-miscible anionic polymer;
- (c) a physiologically acceptable water-miscible non-ionic polymeric viscosity controlling agent; and
- (d) water.

24. A method as claimed in claim 23, wherein said angiogenic polypeptide growth factor is selected from basic fibroblast growth factor and vascular endothelial cell growth factor.

25. A method as claimed in claim 23, wherein said angiogenic polypeptide growth factor is basic fibroblast growth factor.

26. A method as claimed in claim 23, wherein said growth factor is basic fibroblast growth factor.

27. A method as claimed in claim 23, wherein said water-miscible anionic polymer is selected from sodium carboxymethylcellulose and poly(acrylic acid).

28. A method as claimed in claim 23, wherein said water-miscible anionic polymer is poly(acrylic acid).

29. A method as claimed in claim 23, wherein said water-miscible non-ionic polymeric viscosity controlling agent is a polyoxyethylene-polyoxypropylene block copolymer having a molecular weight from about 5,000 Da to about 15,000 Da.

30. A method as claimed in claim 23, wherein said anionic polymer is present in an amount from about 0.001% to about 0.1% by weight of said composition.

31. A method as claimed in claim 23, wherein said non-ionic polymeric viscosity controlling agent is present in an amount from about 0.5% to about 25% by weight of said composition.

32. A method as claimed in claim 23, wherein the ischemic condition being treated is peripheral vascular disease.

33. A method as claimed in claim 23, wherein the ischemic condition being treated is coronary artery disease.

34. A method as claimed in claim 32, wherein the angiogenic growth factor is selected from basic fibroblast growth factor and vascular endothelial cell growth factor.


35. A method as claimed in claim 33, wherein the angiogenic growth factor is selected from basic fibroblast growth factor and vascular endothelial cell growth factor.

5 36. A method as claimed in claim 33, wherein the angiogenic growth factor is basic fibroblast growth factor.


37. A method as claimed in claim 33, wherein the angiogenic growth factor is basic fibroblast growth factor.

10


1 / 6

**Fig. 1**


2 / 6

**Fig. 2**


3 / 6


**Fig. 3**


4 / 6

**Fig. 4**

5 / 6

Release of bFGF from the gels (0.4 mg/mL bFGF)**Fig. 5**

Release of bFGF from the gels (4 mg/mL bFGF)**Fig. 6**



PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : A61K 47/10, 47/32, 47/36, 38/18	A3	(11) International Publication Number: WO 00/13710 (43) International Publication Date: 16 March 2000 (16.03.00)
(21) International Application Number: PCT/US99/20382 (22) International Filing Date: 3 September 1999 (03.09.99) (30) Priority Data: 60/099,168 4 September 1998 (04.09.98) US (71) Applicant (for all designated States except US): SCIOS INC. [US/US]; 820 West Maude Avenue, Sunnyvale, CA 94086 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): JENNINGS, Robert, N., Jr. [US/US]; 5536 Blossom Dale Drive, San Jose, CA 95124 (US). YANG, Bing [CN/US]; 802 Kraken Lane, Redwood City, CA 94065 (US). PROTTER, Andrew, A. [US/US]; 185 California, Palo Alto, CA 94301 (US). WANG, Yu-Chang, John [US/US]; 1421 Baypoint Drive, Newport Beach, CA 92660 (US). (74) Agent: DREGER, Ginger, R.; Knobbe, Martens, Olson and Bear, LLP, 16th Floor, 620 Newport Center Drive, Newport Beach, CA 92660 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> (88) Date of publication of the international search report: 2 June 2000 (02.06.00)
(54) Title: HYDROGEL COMPOSITIONS FOR THE CONTROLLED RELEASE ADMINISTRATION OF GROWTH FACTORS		
(57) Abstract Compositions and methods are disclosed for the controlled release delivery of polypeptide growth factors. The compositions of the invention are hydrogels which comprise: a polypeptide growth factor having at least one region of positive charge; a physiologically acceptable water-miscible anionic polymer; a physiologically acceptable non-ionic polymeric viscosity controlling agent; and water.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/20382

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61K47/10 A61K47/32 A61K47/36 A61K38/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CHEMICAL ABSTRACTS, vol. 124, no. 16, 15 April 1996 (1996-04-15) Columbus, Ohio, US; abstract no. 211858, LEE, YOO-CHEOL ET AL: "Formulation of water-soluble topical preparations of epidermal growth factor" XP002132165 abstract & YAKCHE HAKHOECHI (1995), 25(3), 177-84 ,	1,2,6, 12,13, 16,22
A	FR 2 644 066 A (THERAPEUTIQUES SUBSTITUTIVES) 14 September 1990 (1990-09-14) examples -/-	1-37

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"G" document member of the same patent family

Date of the actual completion of the international search

3 March 2000

Date of mailing of the international search report

16/03/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Boulois, D

INTERNATIONAL SEARCH REPORT

Int. Appl. No.

PCT/US 99/20382

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 312 208 A (ETHICON INC) 19 April 1989 (1989-04-19) cited in the application the whole document	1-37
A	EP 0 551 626 A (LEK TOVARNA FARMACEVTSKIH) 21 July 1993 (1993-07-21) claims	1-37

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 99/ 20382

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
Remark: Although claims 12-37 are directed to a method of treatment of the human/animal body, the search has been carried out and based on the alleged effects of the compound/composition.
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/20382

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2644066 A	14-09-1990	AT 106743 T	15-06-1994
		AU 5283890 A	09-10-1990
		CA 2048638 A	10-09-1990
		DE 69009748 D	14-07-1994
		DE 69009748 T	22-09-1994
		DK 462194 T	19-09-1994
		EP 0462194 A	27-12-1991
		ES 2057544 T	16-10-1994
		WO 9010456 A	20-09-1990
		JP 4505756 T	08-10-1992
		US 5693625 A	02-12-1997
EP 0312208 A	19-04-1989	AU 2223588 A	23-03-1989
		GR 88100617 A,B	22-06-1989
		JP 2000112 A	05-01-1990
		MX 169808 B	27-07-1993
		NZ 226171 A	26-06-1990
		PT 88541 A	31-07-1989
		US 5457093 A	10-10-1995
		US 5705485 A	06-01-1998
		US 5427778 A	27-06-1995
		ZA 8806947 A	30-05-1990
EP 0551626 A	21-07-1993	CA 2085690 A	20-06-1993
		JP 5262670 A	12-10-1993